

5

Claims

1. A liquid crystal material, comprising at least one negative-type mesogen comprising at least one soluble, dipolar dopant.

10 2. A liquid crystal material according to claim 1, wherein the dopant is organic and comprises at least one fluorinated group and/or at least one cyano end group.

15 3. A liquid crystal material according to claim 1 or 2, wherein the negative-type mesogen is selected from the group comprising MLC-2038, MLC-6608, MLC-6609 and MLC-6610.

4. A liquid crystal material according to any of claims 1 to 3, wherein the dopant is present in an amount of between about 0.01 to about 10wt% of the mixture.

20 5. A liquid crystal material according to any of claims 1 to 4, wherein the dopant is present in an amount of between about 0.05 to about 5wt% of the mixture.

25 6. A liquid crystal material according to any of claims 1 to 5, wherein the dopant is present in an amount of about 0.1 to about 1.5wt% of the mixture.

7. A liquid crystal material according to any of claims 1 to 6, wherein the dopant is selected from the group consisting of FMor2, J6, J6a, J10B, J21, 5DCNQ1 and 13FPHPIP.

30 8. A liquid crystal cell or a negative-type liquid crystal display, comprising a liquid crystal material according to any of claims 1 to 7.

9. A method of producing a liquid crystal material, comprising mixing at least one negative-type mesogen with a soluble, dipolar dopant.

35

10. A method according to claim 9, wherein the dopant is organic and comprises at least one fluorinated group and/or at least one cyano end group.
- 5 11. A method according to claim 9 or 10, wherein the negative-type mesogen is selected from the group comprising MLC-2038, MLC-6608, MLC-6609 and MLC-6610.
12. A method according to any of claims 9 to 11, wherein the dopant is admixed in an amount of between about 0.01 to about 10wt% of the final mixture.
- 10 13. A method according to any of claims 9 to 12, wherein the dopant is admixed in an amount of between about 0.05 to about 5wt% of the final mixture.
14. A method according to any of claims 9 to 13, wherein the dopant is admixed in an amount of about 0.1 to about 1.5wt% of the final mixture.
- 15 15. A method according to any of claims 9 to 14, wherein the dopant is selected from the group consisting of FMor2, J6, J6a, J10B, J21, 5DCNQ1 and 13FPHPIP.
- 20 16. A method of producing liquid crystal cells or negative-type crystal displays according to claim 8 comprising the steps of a) mixing at least one negative-type mesogen and about 0.01 to about 10wt% of at least one soluble, dipolar dopant, b) centrifuging the mixture, c) filling cells with the mixture and, d) annealing the filled cells.
- 25 17. A method of improving the response times, homogenous on-state alignments and contrast of a negative-type liquid crystal material without degrading the off-state, comprising adding at least one soluble, dipolar dopant to said liquid crystal material.
18. A method according to claim 17, wherein the dopant is organic and comprises at least one fluorinated group and/or at least one cyano end group.
- 30 19. A method according to claim 17 or 18, wherein the dopant is added in an amount of between about 0.01 to about 10wt% of the negative-type liquid crystal material.

20. A method according to any of claims 17 to 19, wherein the dopant is admixed in an amount of between about 0.05 to about 5wt% of the negative-type liquid crystal material.

5 21. A method according to any of claims 17 to 20, wherein the dopant is admixed in an amount of about 0.1 to about 1.5wt% of the negative-type liquid crystal material.

22. A method according to any of claims 17 to 21, wherein the dopant is selected from the group consisting of FMor2, J6, J6a, J10B, J21, 5DCNQ1 and 13FPHPIP.

10

23. Use of a liquid crystal material according to any of claims 1 to 7 in an improved LC-material for display applications.